

HIGH TEMPERATURE PAINT SPECIFICATION



APPLICATION DATA S10.02-6

Page 1

January, 2008

Supersedes January, 2005

Name: Tnemec Series 39 - 1261 Silicone Aluminum

Material: Silicone Aluminum

Color: Aluminum

Application: Spray as is

% Solids by Volume: 25% \pm 2.0%

Theoretical coverages: 400 mil sq. ft. per gallon

Air Drying Time @ 75° F (24° C):

 Handling: 6 hours

 To re-coat: 12 hours

VOC: 5.32 lbs/gal.

Minimum Surface Prep: SSPC-SP-10

Flash Point: 79° F (26° C)

Performance Criteria: Temperature Resistance (Dry): Continuous 1,200° F (649° C)

Sartell Valves & Controls Standard Thickness: 1-2 mils