



STANDARD PAINT SPECIFICATION

Name: 4D566 Blue Semi-Gloss Water Reducible Enamel
Material: Modified Alkyd
Viscosity: 44" - 50" seconds #3 Zahn @ 77° F (25° C).
Reduction: None
Application: Spray as is
% Solids by Weight: 47.5 ± 2% min.
% Solids by Volume: 32% min.
Gloss: 40 - 50
Theoretical coverages: 400/425 @ 1.5 to 2.0 mils
Air Drying Time @ 77°F (25° C):
 Set to Touch: 20 - 30 min.
 Dry to Handle: 1 hour
 Dry to Hard: 4 hours
VOC: 2.98 lbs/gal.
Mandrel Flexibility: Good
Knife Flexibility: Good
Impact Flexibility: Good
Salt Spray: 5% salt spray @ 95% humidity for 400 hrs (no rust)
Recoatibility: Accepts all types of top coats, e.g. epoxy, coal tar epoxy, vinyl, phenolic, asphaltic, urethane, rubber base and zinc chromate (no zinc filler).
DeZURIK Standard Thickness: 1.5 - 2 mils
12 oz. Aerosol Spray Can PN 1206694 (touch-up)